



American Helicopter Society's  
73<sup>rd</sup> Annual Forum  
May 9-11, 2017



# Hybrid Gear Performance Under Loss-of-Lubrication Conditions

Kelsen E. LaBerge (ARL), Stephen P.  
Berkebile (ARL), Robert F. Handschuh  
(NASA), Gary D. Roberts (NASA)



- **Background**
- **Hybrid gear design**
- **Experimental setup**
- **Results**
- **Conclusions**
- **Future work**



## **What is a hybrid composite gear?**

- **Hybrid composite gear replaces the structural steel portion of a gear with a lightweight composite material**

## **Why hybrid gears?**

- **Hybrid gears offer a potential to increase the power density in drive systems.**
- **Advanced vertical lift configurations are pushing for multi-speed capability, requiring additional driveline components**



U.S. ARMY  
**RDECOM**

## Past Efforts



### Small-Scale



**3.5 inch pitch diameter hybrid  
gears**

- One million cycle endurance test
- Static torque test

### Large-Scale



**16.5 inch pitch diameter hybrid  
bull gear**

- One million cycle endurance test at 3300 hp
- Operational testing at 5000 hp
- Static torque test on the web





U.S. ARMY  
**RDECOM**




What about operation  
under adverse  
conditions?




U.S. ARMY  
**RDECOM**

# Hybrid Gear Design



## Triaxial Braid Architecture




- T700S-50C standard modulus fiber
- Prepreg / compression molding approach for flat web element
- ACG MTM45-1 resin with MTA241 film adhesive



U.S. ARMY  
**RDECOM**



# History



- Gears were reground to correct distortion caused by the curing process – **Resulted in increased backlash**
- Endurance test (10,000 RPM, 490 in-lb) completed to  $10^9$  cycles
- Two hybrid gears used, no damage detected after endurance test

## Procedure

- Green Run at 10,000 RPM and 210 in-lb for at least 1 hour
- Increase torque to 520 in-lb
- At thermal equilibrium turn off oil supply pump and cap supply line
- Continue test until failure



**Contact Fatigue Test Rig at NASA  
Glenn Research Center**






U.S. ARMY  
**RDECOM**

UNCLASSIFIED


# Results - Baseline





## Steel Driving Steel (Unshrouded)



— Out of Mesh      — Left Gear      — Right Gear




## Hybrid Driving Hybrid




- After shutdown loss-of-torque was verified
- Visual inspection showed that the hub had rotated with respect to the teeth on the left gear

## Disassembled left gear



## Modified right gear



Approximate location of  
interlock pattern






U.S. ARMY  
**RDECOM**

UNCLASSIFIED

## Experiment 2









U.S. ARMY  
**RDECOM**

UNCLASSIFIED


## Results - Experiment 2





## Stop 1

- Torque transfer verified
- Black lines documented on teeth
- Restarted experiment dry and reapplied load






U.S. ARMY  
**RDECOM**


UNCLASSIFIED

## Results - Experiment 2



### Stop 2

- Torque transfer verified
- Gears photographed
- Restarted experiment dry and reapplied load






U.S. ARMY  
**RDECOM**

UNCLASSIFIED

## Results - Experiment 2







U.S. ARMY  
**RDECOM**


## Post-test Analysis




# What is the source of the black substance on the gear teeth?

- **Samples collected**
  - Gear teeth
  - Gearbox
  - Uncured prepreg
  - Thin film adhesive
- **Analyzed using energy dispersive spectroscopy for elemental characterization**


## Gear Tooth Surface Sample




## Gearbox Residue Sample



## Epoxy on Prepreg



## Thin Film Adhesive






- The mechanical interlock design in a hybrid gear is important during an oil-out event
- The pinned interlock pattern was shown to better withstand this type of event
- At increased temperatures, softened polymer at the gear mesh may act as a lubricant or sulfur-containing lubricant additive

**The effects of material degradation on hybrid gear design for oil-out conditions needs further investigation**





- **Isolate source of performance increase**
  - Increased backlash
  - Polymer lubricant
- **Can polymer flow phenomenon be used to increase survivability of steel gears during an oil-out event?**





U.S. ARMY  
**RDECOM**



# Questions?



A&P Technology



## Acknowledgements:

- A&P Technology – Provided hybrid gears used for this project as part of a NASA SBIR
- Roger Tuck – Technician support
- ARL's Weapons and Materials Research Directorate – EDS